

• TRUSTED QUALITY SINCE 1921 •



SPECIALTY APPLIANCE TOUCH-UP PAINT

DESCRIPTION AND USES

Rust-Oleum® Specialty Appliance Touch Up Paint is a quick dry lacquer designed to provide a long-lasting, high gloss finish on repairs to metal, porcelain, and appliances such as stoves, refrigerators, washers, dryers, and dishwashers. This washable, moisture resistant finish is for the exteriors of these surfaces. Do not use on surfaces exposed to temperatures over 200°F (93°C) such as stove tops. Not for use in sinks, tubs, or other water immersed surfaces.

PRODUCTS

FINISHES

203000	White
2030001	Almond
203002	Biscuit
213174	Black

PRODUCT APPLICATION

PAINTING CONDITIONS

Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C).

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. LEAD IS TOXIC. Contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Apply Appliance Touch Up using even strokes. For deep scratches or chips, apply multiple layers allowing 10 minutes between coats. For best results, allow to dry overnight before use.

PRODUCT APPLICATION (cont.)

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 10 minutes, to handle in 30 minutes and fully dry in 24 hours. Allow to dry 10 minutes between coats.

CLEAN-UP

Clean up any excess product with lacquer thinner, rubbing alcohol, or acetone.

PHYSICAL PROPERTIES

		APPLIANCE TOUCH-UP PAINT
Resin Type		Acrylic Lacquer
Pigment Type		Varies with Color
Weight - per Gallon		8.2-9.3 lbs.
per Liter		1.0-1.1 kg
Solids by Weight		28.1-36.7%
Solids by Volume		22.6-23.0%
Volatile Organic Compounds		<710 g/l (5.90 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		2.0-4.0 mils (varies with depth of scratch) (50-100μ)
Wet Film to Achieve DFT (unthinned material)		9.0-18.0 mils (225-450μ)
Theoretical Coverage at 1 mil DFT (25μ)		1.7 sq.ft./bottle (0.6 ounces)
Practical Coverage at Recommended DFT (assumes 15% material loss)		0.25-0.5 sq.ft./bottle (0.6 ounces)
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	10 minutes
	Handle	20 minutes
	Recoat	10 minutes
	Full Cure	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		3 years
Flash Point		57°F (14°C)
Warning!		For additional information, see MSDS.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.